

# Gelacquer™

## Application Instructions



1. Sanitize and prep the nails as usual. Using **BASIC ONE Wiping Solution** to cleanse all ten nails thoroughly. Wait until nails are completely dry.
3. Brush on a thin coat of **Permashine** or **Builder Gelacquer** to all ten nails, then cure under UV Lamp for three minutes.
4. Polish on a thin coat of desired **Gelacquer** color(s) to all ten nails then cure for three minutes. Apply another layer/coat of Gelacquer color if desired, cure under **BASIC ONE UV Lamp** for three minutes.
5. Polish a thin coat of **Permashine** to all ten nails, cure under **BASIC ONE UV Lamp** for three minutes.
6. Remove sticky residue with **BASIC ONE Wiping Solution** and your client is free to go!

---

### SOAK OFF INSTRUCTIONS

1. Buff the shine off the surface of the nails.
2. Place all ten fingers in a bowl of 100% pure acetone for 5-10 minutes depending on the thickness of the gel.
3. While the nails are in the bowl with fingers pointed down, take an orange woodstick and gently push on the loosened gel downwards toward the bottom of the bowl. The gel does not disintegrate in the acetone like acrylic polymer/powder does. It softens with acetone and can be removed easily.

---

*Please Note:*

*\*If entire gel nails are soft and peel off within hours/days, this means that the nails were under cured.*

*\*If nails break/crack, are bendable, or chip/crack; this means that the gel application was too thin.*

*\*If gel lifts around cuticle area, this means lack of prepping. If necessary-for oilier nails, wipe with Wiping Solution twice prior to gel application.*

*\*\*For technical support, please call us anytime during business hours.*