




GELACQUER PERMASHINE TUTORIAL

STEP BY STEP • HOW TO TUTORIAL



1. Sanitize and prep nails as usual. Using Basic One Wiping Solution to cleanse all ten nails thoroughly. Wait until nails are completely dry.

2. Brush on a thin coat of Permashine or Gelacquer Clear Builder to all ten nails, then cure under an LED/UV Lamp for 1-3 minutes.

3. Polish on a thin coat of desired Gelacquer color to all ten nails then cure for 1-3 minutes. Apply another layer/coat of Gelacquer Soak-Off Gel if desired and then cure under an LED/UV Lamp for 1-3 minutes.

4. Brush on a thin layer of pink gel to the bed of nail and stop at the smile line of white gel. Cure nails for one minute and alternate fingers.

5. Polish a thin coat of Permashine to all ten nails, cure under an LED/UV Lamp for 1-3 minutes.

6. Remove the sticky residue with our Basic One Wiping Solution. Use our Cuticle Oil to finish this set.

Soak-Off Instructions:

1. Buff the shine off the surface of the nails

2. Place all ten fingers in a bowl of 100% pure acetone for 5-10 minutes, depending on the thickness of the gel.

3. While the nails are in the bowl, take an orange woodstick and gently push on the loosened gel downwards towards the bottom of the bowl. The gel does not disintegrate in the acetone like acrylic polymer does. It softens with acetone and can easily be removed.

Please Note:

• If entire gel nails are soft and peel off within hours/days, this means that the nails were under cured.

• If nails break/crack, are bendable, or chip/crack; this means that the gel application was too thin.

• If gel lifts around cuticle area, this means lack of prepping. If necessary, for oily nails, wipe with Wiping Solution twice prior to gel application.

For technical support, please call us anytime during business hours at **(951) 808-4730**.